# productinformation

# tesa® 4952

# 1150 µm double sided PE foam tape

tesa® 4952 is a double sided PE foam tape for constructive mounting applications. It consists of a highly conformable PE foam backing and a tackified acrylic adhesive. tesa® 4952 has been externally certified for furniture mirror mounting.

#### Product benefits:

- Versatile adhesive for high immediate adhesion on numerous substrates
- Fully outdoor suitable: UV, water and ageing resistant
- Compensates for differing thermal expansion of dissimilar materials
- High immediate bonding strength even at low bonding pressure
- Very good cold shock absorbtion

## Main Application

- Furniture mirror mounting
- Mounting of car mirrors
- Mounting functional trims & profiles
- Mounting of decorative panels

#### Technical Data

•	Backing material	PE foam	•	Tensile strength	10 N/cm
•	Color	white	•	Type of liner	glassine
•	Total thickness	1150 μm	•	Colour of liner	brown
•	Type of adhesive	tackified acrylic	•	Thickness of liner	70 μm
•	Elongation at break	200 %		Weight of liner	80 g/m <sup>2</sup>

#### Adhesion to

•	Steel (initial)	6.5 N/cm	•	Steel (after 14 days)	8.0 N/cm
•	ABS (initial)	5.0 N/cm	•	ABS (after 14 days)	8.0 N/cm
•	Aluminium (initial)	5.0 N/cm	•	Aluminium (after 14 days)	8.0 N/cm
•	PC (initial)	5.0 N/cm	•	PC (after 14 days)	8.0 N/cm
•	PE (initial)	2.7 N/cm	•	PE (after 14 days)	2.8 N/cm
	PET (initial)	5.0 N/cm	•	PET (after 14 days)	7.0 N/cm
	PP (initial)	2.8 N/cm	•	PP (after 14 days)	5.5 N/cm
•	PS (initial)	5.0 N/cm	•	PS (after 14 days)	7.5 N/cm
•	PVC (initial)	5.0 N/cm	•	PVC (after 14 days)	8.0 N/cm

For latest information on this product please visit <a href="http://l.tesa.com/?ip=04952">http://l.tesa.com/?ip=04952</a>

# tesa® 4952

# 1150 µm double sided PE foam tape

## **Properties**

•	lemperature	resistance short term	
	T	and the second of the second of the second	

Temperature resistance long term

Tack

Ageing resistance (UV)

Humidity resistance

80°C 80°C Resistance to chemicals

Softener resistance

Static shear resistance at 23°C

Static shear resistance at 40°C

Evaluation across relevant tesa® assortment: • • • • very good

good

medium

low

#### Additional Information

tesa® 4952 has been tested and approved by LGA institute for mirror mounting. Report number IWQ FSG 329 1189.

#### Peel Adhesion:

- immediately: foam splitting on Steel, Aluminium, ABS, PC, PS, PET, PVC
- after 14 days: foam splitting on Steel, Aluminium, ABS, PC, PS, PET, PVC