

## tesa® 51970

### Transparent double-sided filmic tape

tesa® 51970 is a transparent double-sided tape consisting of a PP-film backing and a tackified adhesive.

tesa® 51970 features especially:

- Excellent combination of high tack and adhesion
- Secure bond even on critical materials such as PP and PE and rough surfaces
- Good temperature resistance and outdoor suitability

### Main Application

- Mounting of plastic and wooden trims
- Mounting of decorative materials and displays
- Mounting of transparent signs and scales

### Technical Data

▪ Backing material	PP film	▪ Tensile strength	50 N/cm
▪ Color	transparent	▪ Type of liner	glassine
▪ Total thickness	220 µm	▪ Colour of liner	brown
▪ Type of adhesive	tackified acrylic	▪ Thickness of liner	71 µm
▪ Elongation at break	150 %		

### Adhesion to

▪ Steel (initial)	13.0 N/cm	▪ Steel (after 14 days)	13.5 N/cm
▪ ABS (initial)	11.3 N/cm	▪ ABS (after 14 days)	14.4 N/cm
▪ Aluminium (initial)	10.2 N/cm	▪ Aluminium (after 14 days)	12.8 N/cm
▪ PC (initial)	12.3 N/cm	▪ PC (after 14 days)	15.0 N/cm
▪ PE (initial)	5.4 N/cm	▪ PE (after 14 days)	6.8 N/cm
▪ PET (initial)	9.9 N/cm	▪ PET (after 14 days)	12.5 N/cm
▪ PP (initial)	6.8 N/cm	▪ PP (after 14 days)	8.8 N/cm
▪ PS (initial)	11.8 N/cm	▪ PS (after 14 days)	13.4 N/cm
▪ PVC (initial)	10.5 N/cm	▪ PVC (after 14 days)	17.0 N/cm

For latest information on this product please visit <http://l.tesa.com/?ip=51970>

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All technical information and data above mentioned are provided to the best of our knowledge on the basis of our practical experience. They shall be considered as average values and are not appropriate for a specification. Therefore tesa SE can make no warranties, expressed or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. The user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.

## tesa® 51970

### Transparent double-sided filmic tape

#### Properties

▪ Temperature resistance short term	130 °C	▪ Softener resistance	● ● ●
▪ Temperature resistance long term	80 °C	▪ Static shear resistance at 23°C	● ● ●
▪ Tack	● ● ●	▪ Static shear resistance at 40°C	● ● ●
▪ Ageing resistance (UV)	● ● ●		
▪ Humidity resistance	● ● ● ●		
▪ Resistance to chemicals	● ● ●		

Evaluation across relevant tesa® assortment: ● ● ● ● very good ● ● ● good ● ● medium ● low

#### Additional Information

Liner variants:

PV0 brown glassine paper (71 µm)

PV1 white paper liner (84 µm; 100gr/m²)

PV6 red MOPP-film (80 µm)

A fingerlift version (extended liner), tesa® 61970, is also available.

According to VDA278 analysis, tesa 51970 does not contain any single substances restricted by the drafted GB regulations (China) as well as the indoor concentration guideline by Health, Labour and Welfare Ministry (Japan).

For latest information on this product please visit <http://l.tesa.com/?ip=51970>

tesa® products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All technical information and data above mentioned are provided to the best of our knowledge on the basis of our practical experience. They shall be considered as average values and are not appropriate for a specification. Therefore tesa SE can make no warranties, expressed or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. The user is responsible for determining whether the tesa® product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.