productinformation

tesa[®] 4961 Double-sided tape with paper backing

tesa[®] 4961 consists of a natural rubber adhesive and special paper backing. The "hard" adhesive system provides good shear resistance and can also be removed without leaving adhesive residues.

Main Application

Technical Data

- Splicing of paper and film
- Self-adhesive mounting of sanding discs
- General mounting on smooth surfaces

| rechnical Data | | | | | | | | |
|-------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|----------------------------------------------------------------------------------------------------------|-------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|----------------------------------------------------------------------------------------------|--|--|--|--|--|
| Backing material Color Total thickness Type of adhesive | flat paper white 205 μm natural rubber | Elongation at break Tensile strength Type of liner Colour of liner | 3 % 90 N/cm glassine brown | | | | | |
| Adhesion to | | | | | | | | |
| Steel (initial) ABS (initial) Aluminium (initial) PC (initial) PE (initial) PET (initial) PP (initial) PS (initial) PVC (initial) | 7.8 N/cm 6.0 N/cm 6.1 N/cm 7.3 N/cm 3.9 N/cm 5.7 N/cm 5.4 N/cm 7.0 N/cm 6.2 N/cm | Steel (after 14 days) ABS (after 14 days) Aluminium (after 14 days) PC (after 14 days) PE (after 14 days) PET (after 14 days) PP (after 14 days) PS (after 14 days) PVC (after 14 days) | 8.0 N/cm 6.6 N/cm 7.5 N/cm 4.1 N/cm 5.8 N/cm 6.7 N/cm 7.7 N/cm 6.3 N/cm | | | | | |
| Properties | | | | | | | | |
| | | | | | | | | |

| • | Temperature resistance short term | 110 °C | | Resistance to chemicals | •• |
|----|------------------------------------------------------|-------------------|---|---------------------------------|-----|
| • | Temperature resistance long term | 40 °C | | Softener resistance | •• |
| • | Tack | ••• | | Static shear resistance at 23°C | •• |
| • | Ageing resistance (UV) | • • | | Static shear resistance at 40°C | • • |
| • | Humidity resistance | •• | | | |
| Ev | aluation across relevant tesa [®] assortmen | t: •••• very good | • | ● good ● ● medium ● low | |

²age 1 of 1 - As of 28/06/2017

en

For latest information on this product please visit <u>http://l.tesa.com/?ip=04961</u>

tesa[®] products prove their impressive quality day in, day out in demanding conditions and are regularly subjected to strict controls. All technical information and data above mentioned are provided to the best of our knowledge on the basis of our practical experience. They shall be considered as average values and are not appropriate for a specification. Therefore tesa SE can make no warranties, expressed or implied, including, but not limited to any implied warranty of merchantability or fitness for a particular purpose. The user is responsible for determining whether the tesa[®] product is fit for a particular purpose and suitable for the user's method of application. If you are in any doubt, our technical support staff will be glad to support you.

